

Amendments to the Specification

Please amend page 5, lines 4-10, in the DISCLOSURE OF THE INVENTION as set forth below.

(B) when a square test piece cut off from the heat-shrinkable polyester film in a size of 10 cm x 10 cm is immersed in hot water at 85°C for ~~40~~ 5 seconds, subsequently in water at 25°C for 10 seconds, and withdrawn, the heat shrinkage percentage of the test piece in the maximum shrinkage direction is 70% or more and that in the direction orthogonal thereto, 10% or less; and